



7815EH 3M TT5 MW PET 50-310E-90WG

Thermal Transfer Polyester Label Material

Provisional Data Sheet

Issued : **June 2004**
(Provisional)
Supersedes : **May 2003**
(Provisional)

Physical Properties
Not for specification purposes
(Calipers are nominal values)

Facestock	55 micron Matte Radiant White polyester
Adhesive	20 micron #310 E Acrylic
Liner	77 micron, 90 g/m ² White Densified Glassine
Shelf Life	24 months from date of manufacture of product when properly stored at 22°C and 50% relative humidity.

Features:

- TT5 Matte topcoat provides a smooth matte surface, giving excellent thermal transfer images at reduced burn temperature settings, resin ribbons are recommended for optimum durability. The matte coating is extremely resistant to degradation from scuffing, chemicals, moisture, and wide temperature fluctuations. The topcoat also provides improved ink anchorage for traditional forms of press printing.
- 310 E is a firm adhesive, which resists oozing and provides high strength on a variety of surfaces including high surface energy (HSE) plastics and metals. It additionally has improved chemical and U.V resistance.
- 90 g/m² densified glassine liner assures consistent die cutting.
- 3M™ Label Material 7815EH is UL and cUL Listed (File No. MH18072)

Application Ideas:

- Barcode labels and rating plates.
- Property identification and asset labelling.
- Warning, instruction, and service labels for durable goods.
- Nameplates for durable goods.

Performance Characteristics
 Not for specification purposes

Adhesion	90°Peel Adhesion, Test procedure FTM 2			
	Initial (20 Minute Dwell/RT)		Ultimate Adhesion 72 Hours Dwell at Maximum UL Temperature rating	
	N/10mm	Oz/In	N/10mm	Oz/In
Aluminium	3.1	28	6.4	58
Stainless Steel	4.7	43	6.8	62
Phenolic	3.1	28	4.7	43
ABS	3.4	31	3.2	29
Polycarbonate	2.5	23	3.1	28
Polystyrene	3.7	34	4.5	41
Polypropylene	0.5	4.6	1.8	16
HD Polyethylene	1.8	16	3.2	29
LD Polyethylene	0.9	8.2	1.3	12
Powder Coating	3.7	34	6.4	31

Surface	Conditioned for 3 Days at - 40°C	
	90° Peel	
	N/10mm	Oz/In
Aluminium	2.8	25
Stainless Steel	5.9	54
Phenolic	4.0	36
ABS	4.6	42
Polycarbonate	3.3	42
Polystyrene	4.5	41
Polypropylene	1.1	10
HD Polyethylene	2.0	18
LD Polyethylene	1.3	12
Powder Coating	3.3	30

Performance Characteristics Contd.
 Not for specification purposes

	180°Peel Adhesion, Test procedure FTM 1			
	Initial (20 Minute Dwell/RT)		Ultimate Adhesion 72 Hours Dwell at Maximum UL Temperature rating	
	N/10mm	Oz/In	N/10mm	Oz/In
Aluminium	4.2	38	6.7	61
Stainless Steel	4.5	41	8.7	80
Phenolic	4.8	44	8.7	80
ABS	5.2	47	6.0	55
Polycarbonate	5.1	46	4.2	38
Polystyrene	4.8	44	4.8	44
Polypropylene	0.4	3.6	3.1	28
HD Polyethylene	0.4	3.6	3.0	27
LD Polyethylene	0.4	3.6	0.8	7.5

	Conditioned for 3 Days at - 40°C	
Surface	180° Peel (FTM 1)	
	N/10mm	Oz/In
Aluminium	4.7	43
Stainless Steel	7.0	64
Phenolic	5.0	46
ABS	4.9	45
Polycarbonate	5.8	53
Polystyrene	4.8	44
Polypropylene	0.6	5.5
HD Polyethylene	0.4	3.6
LD Polyethylene	0.4	3.6

Liner Release	FTM 3 180° Removal of Liner from Facestock		
	Rate of Removal	N/10mm	Gms/50mm Width
	2.3 m / min	0.025	13

Environmental Performance	The properties defined are based on four hour immersions at room temperature 22°C unless otherwise noted. Samples were applied to stainless steel panels 24 hours prior to immersion and were evaluated one hour after removal from the solution for peel adhesion. Adhesion measured at 90° peel angle (FTM 2 at 305 mm/min).				
Chemical Resistance	Adhesion to Stainless Steel			Appearance	Edge Penetration
Chemical	N/10mm	Oz/In	% Change	Visual	Millimetres
Isopropyl Alcohol	5.4	49	90	No change	1
Detergent (1% Alconox®*)	5.5	51	104	No change	1
Engine Oil (10W30) @ 250°F (121°C)	5.7	52	106	No change	1
Water for 48 hours	5.7	52	106	No change	0
pH 4	5.8	53	107	No change	0
PH10	5.8	53	107	No change	0
Toluene	3.1	28	57	Topcoat Damaged	5.0
Acetone	3.0	27	56	Topcoat Damaged	6.0
Brake Fluid	5.3	48	98	Slight Damage	1
Gasoline	3.8	35	70	No change	5.0
Diesel Fuel	4.6	42	85	No change	0
Naphtha	3.2	29	59	No change	3.0
Hydraulic Fluid	5.6	51	103	No change	0

Temperature Resistance	149°C for 24 hours:	no significant visual change 0.7% MD shrinkage 0.9% CD shrinkage
	-40°C for 3 days:	no significant visual change
Humidity Resistance	24 hours at 38°C and 100% relative humidity	no significant changes in appearance or adhesion

Agency Listing Information

Thermal Transfer Printing:

Face Stock is UL and cJUL approved with the following ribbons

Armor: AXR 7+; AXR 8; AXR 600
Ricoh™: B110C; B110CX; B110CR; B120EC
Sony™: TR4070; TR5070; TR4570
Astromed: RY
Kurz: 501
Zebra: 4800, 5095, 5100

Processing

Printing:

Facestock is topcoated for improved ink receptivity and is designed for thermal transfer printing. It is printable by all standard roll processing methods including flexography, hot stamp, letterpress, and screen printing.

Die Cutting:

Rotary die cutting is recommended. Fanfolding of labels is not recommended. Small labels should be evaluated carefully. Winding tensions should be kept at a minimum to help prevent the adhesive from oozing.

Packaging:

Finished labels should be stored in plastic bags.

Special Considerations

For maximum bond strength, the surface should be clean and dry. Typical cleaning solvents are heptane and isopropyl alcohol.

NOTE: When using solvents, read and follow the manufacturer's precautions and directions for use.

For best bonding conditions, application surface should be at room temperature or higher. Low temperature surfaces, below 5°C can cause the adhesive to become so firm that it will not develop maximum contact with the substrate. Higher initial bonds can be achieved through increased rubdown pressure.

3M is a trademark of the 3M Company.

Values presented have been determined by standard test methods and are average values not to be used for specification purposes. Our recommendations on the use of our products are based on tests believed to be reliable but we would ask that you conduct your own tests to determine their suitability for your applications. This is because 3M cannot accept any responsibility or liability direct or consequential for loss or damage caused as a result of our recommendations.

* Trademarks listed are the property of their respective owners



Tapes & Adhesives Group

© 3M United Kingdom PLC 2004

3M United Kingdom PLC
3M Centre, Cain Road,
Bracknell, Berkshire,
RG12 8HT

Product Information :
Tel 0870 60 800 50
Fax 0870 60 700 99

3M Ireland
3M House, Adelphi Centre,
Upper Georges Street,
Dun Laoghaire, Co. Dublin,
Ireland

Customer Service :
Tel (01) 280 3555
Fax (01) 280 3509